

Datasheet

Polyurethaanplaat 65°

Colour: dark brown	POLYMER: polyesther
---------------------------	----------------------------

Physical properties	Unit	Value	Standard
Hardness	° Shore A	65	DIN
Tensile strength	N/mm ²	33	DIN 53504
Tensile Stress at elong. of 300%	N/mm ²	-	DIN 53504
Tear strength	N/mm	30	DIN 53507
Density, approximately	g/cm ³	1,25	DIN 53479
Rebound resilience	%	40	DIN 53512
Elongation at Tear	%	750	DIN 53504
Abrasion	mm ³	45	DIN 53516

Datasheet

Polyurethaanplaat 90°

Colour: dark brown	POLYMER: polyesther
---------------------------	----------------------------

Physical properties	Unit	Value	Standard
Hardness	° Shore A	90	DIN
Tensile strength	N/mm ²	45	DIN 53504
Tensile Stress at elong. of 300%	N/mm ²	18	DIN 53504
Tear strength	N/mm	70	DIN 53507
Density, approximately	g/cm ³	1,25	DIN 53479
Rebound resilience	%	40	DIN 53512
Elongation at Tear	%	630	DIN 53504
Abrasion	mm ³	35	DIN 53516