

**Datasheet**

Asbestvrije Pakkingsplaat AV 400

<b>MATERIAL: AV 400</b>	<b>POLYMER: Non-asbestos HP packing sheet</b>
-------------------------	---

Physical properties	Unit	Value	Standard
Tensile strength	N/mm <sup>2</sup>	14	
Density, approximately	G/cm <sup>3</sup>	1,6	
Compression set	%	7-17	ASTM F 36A
Pressure (max) bar	Max.	100	
Working temperature range	Max.	400	
Recovery	%	50	ASTM 36A
Colour		Blue	
Gas Permeability	cm <sup>3</sup> /min	0.5	DIN 3754 Pt6
Residual Stress	MPa MPa	25 29	BS 7531 DIN 52913
Thickness increase In ASTM oil no.3, after 5 hrs at 150°C			
In ASTM Fuel B, after 5 hrs at 20°C	% %	0-5 0-7	ASTM F 146 ASTM F 146
Resistance		See chemical resistance list	