

Datasheet
Sponsrubberprofiel EPDM 15°

Material	Ethylen – Propylen – Dienmonomere
Forms	Cords Square profiles Special profiles
Production characteristics	Continuously extruded and vulcanised with closed skin
Colour	Black/grey
Density	400 – 500 kg/m ³
Hardness	15 +/- 5 Shore A
Compression set	25% (ISO 815)
Dimensional tolerances	DIN ISO 3302-1 E3
Resistance	
Temperature	-35°C bis + 110°C
Ageing	Excellent
Weather	Excellent
UV / Ozon	Excellent
Oils and fats	
Vegetable	Good
animal	Moderate
Mineral	Moderate
Solvents	Ketone, Alcohol excellent
Alkaline solution (diluted)	Excellent