

**Datasheet**  
Sponsrubberprofiel EPDM 25°

Material	Ethylen – Propylen – Dienmonomere
<b>Forms</b>	Cords Square profiles Special profiles
<b>Production characteristics</b>	Continuously extruded and vulcanised with closed skin
<b>Colour</b>	Black/grey
<b>Density</b>	600 – 800 kg/m <sup>3</sup>
<b>Hardness</b>	25 +/- 5 Shore A
<b>Compression set</b>	25% (ISO 815)
<b>Dimensional tolerances</b>	DIN ISO 3302-1 E3
<b>Resistance</b>	
<b>Temperature</b>	-35°C bis + 110°C
<b>Ageing</b>	Excellent
<b>Weather</b>	Excellent
<b>UV / Ozon</b>	Excellent
<b>Oils and fats</b>	
<b>Vegetable</b>	Good
<b>animal</b>	Moderate
<b>Mineral</b>	Moderate
<b>Solvents</b>	Ketone, Alcohol    excellent
<b>Alkaline solution (diluted)</b>	Excellent